



Technical Data Sheet

BLEACHED SOFTWOOD KRAFT PULP

Brand:

KomiPrime

Information:

Mill's certificates

- ISO 9001
- ISO 14001
- ISO 45001

Test conditions: Guaranteed values after conditioning measured at $50 \pm 2\%$ RH and $23 \pm 1^\circ\text{C}$ (ISO 187:1990)

System for verifying legal origin of the wood for this product complies with international standard ISO 38200:2018 Chain of custody of wood and wood based products and Forest Certification Legal Origin standard

Parameter	Unit	Test method	C1	Typical values
Brightness	%	ISO 3688	87	88.4
Dirt Count (0.1-1.0 mm ²), not more	points/500 g	GOST 14363.3	25	7
Dirt Count >1.0 mm ²	points/500 g	GOST 14363.3	0	0
Tearing resistance, not less	mH·m ² /g	ISO 1974	8.0	9.1
pH	-	GOST 12523	5.5 - 7.0	6.2
Moisture, not more	%	ISO 638	15	13.0
Breaking Length, not less	km	ISO 1924	7.8	8.6

Product description:

BLEACHED SOFTWOOD KRAFT PULP is designed for the production of various types of paper and cardboard.

Valid until: 31.12.2024 or until further notice