

Technical Data Sheet



Guaranteed Values

White top kraftliner (WTKL)

Brand:

KomiWhite

Parameters	Unit of measure	Test method	Substance (g/m ²)								
			100	110	120	135	160	175	200	250	280
Substance tolerance	g/m ²	ISO 536	100±5	110±5	120±5	135±5	160±5	175±5	200±8	250±10	280±10
Moisture tolerance, min/max	%	ISO 287	7.5±1.5								
Bursting strength, min	kPa	ISO 2759	n/a	420	460	560	680	740	830	950	1065
SCT _{CD} , min	kN/m	ISO 9895	1.80	2.05	2.25	2.60	3.10	3.30	3.70	4.60	5.10
Scott plybond, min	J/m ²	TAPPI 569	200			230			180		
Bendtsen roughness (top side), max	ml/min	ISO 8791-2	250	400			600			1200	1400
Brightness (top side), min	%	ISO 2470	73						78		
Cobb ₆₀ (top side), max	g/m ²	ISO 535	35								
Cobb ₆₀ (bottom side), min/max	g/m ²	ISO 535	30-100								

Information:

Mill's certificates

- ISO 9001
- ISO 14001
- ISO 45001

Test conditions: Guaranteed values after conditioning, measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

System for verifying legal origin of the wood for this product complies with international standard ISO 38200:2018 Chain of custody of wood and wood based products and Forest Certification Legal Origin standard

End-uses:

- Food & beverage packaging
- Promotional packaging
- Industrial packaging

Product description:

Liner for corrugated board

Valid until: 31.12.2024 or until further notice