

Technical Data Sheet



Guaranteed Values

Fully bleached uncoated white kraftliner, also as fluting (with OBA)

Brand:

KomiXBright

Parameters	Unit of measure	Test method	Substance (g/m ²)		
			100	110	120
Substance tolerance	g/m ²	ISO 536	100±3	110±3	120±3
Moisture tolerance, min/max	%	ISO 287	6,0-9,0		
Scott plybond, min	J/m ²	TAPPI 569	230		
SCT _{CD} , min	kN/m	ISO 9895	1,60	1,80	2,00
Cobb60 (top side), max	g/m ²	ISO 535	35		
Bendtsen roughness (top side), max	ml/min	ISO 8791-2	400	400	400
Brightness (top side), min	%	ISO 2470	80		

Information:

Mill's certificates

- ISO 9001
- ISO 14001
- ISO 45001

Test conditions: Guaranteed values after conditioning, measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

System for verifying legal origin of the wood for this product complies with international standard **ISO 38200:2018**
Chain of custody of wood and wood based products and Forest Certification Legal Origin standard

Valid until: 31.12.2024 or until further notice